



adesivi

JOLLY

TECHNICAL DATA SHEET



Review 005, 04/2020

Page 1 di 2

PRODUCT

JOLLY TRANSPARENT and TIXO GOLD (M2137, M4164, M4165)

FEATURES

JOLLY TRANSPARENT (available in liquid and tixo version) is a mastic based on synthetic resins and it is used to plaster all kinds of marbles and natural stones. Thanks to our different available versions, it's easy to apply and always ready to satisfy the different requests.

Very strong, it gets hard and perfectly polishing after the consolidation.

JOLLY TIXO TRANSPARENT GOLD is a transparent creamy mastic with a light-yellow color, right for particular works to do, such as plasting of the travertine, also in vertical position.

TIXO TRANSPARENT version is even more transparent than GOLD version, but it is not suitable for vertical processing.

TECHNICAL DATA

	LIQUID	TIXO GOLD	TIXO TRANSPARENT	
Specific weight	1130 ± 20	1100 ± 20	1070 ± 20	(MI 001)
Viscosity	550 ± 30 cP	900 ± 150 Pas	1100 ± 150 Pas	(MI 002; MI 002B 25°C)
Color	Very transparent	Transparent	Very transparent	light-yellow

STORAGE

Keep the container well closed and stored in a cool (temperature below 25°C) and ventilated environment for a maximum period of 12 months from the date of production marked on the tin. Avoid direct sun exposure.

SAFETY RULES

During the application and the drying time ventilate the place. It is recommended to use the appropriate PPE during the application phase. Read carefully the safety data sheet before application.

APPLICATION

- Make sure that surfaces to be filled are perfectly clean and dry;
- Mix the product;
- Take from the tin the amount to be used with clean tools, adding 1-3 grams of hardener per 100 grams of product;
- Mix the right amount blending the two components;
- Apply JOLLY on the surface to glue or to plaster, and remember that the mastic totally hardens after 30 minutes; the time of hardening will be shorter with temperatures above 25°C and longer with lower temperatures.
- Do not put back hardened and/or unused product into the tin in order to prevent that the entire content get spoiled;
- Close the tin after use, in order to prevent the hardening of the product due to air contact.







ILPA ADESIVI SRL

TECHNICAL DATA SHEET



Review 005, 04/2020

Page 2 di 2

	Application	Putty knife	
	Hardener	1 – 3 % benzoyl peroxide	
	Gel time	4 - 5 min	(MI 003; 25 °C)
	Ready for stacking	10 - 30 min	(MI 012; 25°C)
	Full dry	24 h	(MI 012; 25°C)
	Polishable	After 24 h	(MI 012; 25°C)

ADDITIONAL INFORMATION

Do not apply on wet surfaces to prevent an incomplete hardening.

In order to avoid product browning, do not use hardening more than 3%.