



a d e s i v i

TECHNICAL DATA SHEET



Review 002, 05/2016

Page 1 of 1

PRODUCT

THICKENER (M51126)

FEATURES

THICKENER to be added to the liquid epoxy resin to obtain the most suitable viscosity in relation to type of work. The possibility to add autonomously the needed amount of thickener, allow the user to obtain the product he wants, leaving the features of the resin and the specific weight of the used product unchanged.

TECHNICAL DATA

Specific weight	50 ± 5 g/l	(MI 001)
Color	Iced white	

STORAGE

Keep the container well closed and stored in a cool (temperature below 25°C) and ventilated environment for a maximum period of 12 months from the date of production marked on the tin. Avoid direct sun exposure.

SAFETY RULES

Keep the place ventilated during application and drying processes. The use of personal protective equipment is recommended during application. Read carefully the safety data sheet before application.

APPLICATION

- Add the thickener to the epoxy resin and mix them up until all clumps are eliminated.
- Use 1 – 2% of thickener to obtain a pasty liquid; use 3 – 5 % of thickener to obtain high thickness similar to putty;
- Add the hardener according to the appropriate ratio and mix them all;
- Apply the product and allow the area to dry.

ILPA ADESIVI SRL